

TECHNICAL DATA SHEET **EOS GENTILE STOP-LAM - H100E - G74B**  
PRODUCT CODE: **EL1271A**



**Facestock: EOS GENTILE STOP-LAM**

White smooth and opaque, wet strength and anti-mould, uncoated paper. Thanks to advanced technological and laminated barrier devices, offers excellent resistance and stability to deep ice-bucket standing, preserving good wet label opacity and whiteness. Product designed to produce labels intended for labelling of wine, spirits and food specialties.

|               |     |                   |         |
|---------------|-----|-------------------|---------|
| Basis weight: | 108 | gr/m <sup>2</sup> | ISO 536 |
| Thickness:    | 124 | µm                | ISO 534 |

**Adhesive: H100E**

High performance, permanent rubber based adhesive, specifically designed for labelling of glass bottles in the wine, spirits and olive oil label industry. Allows good adhesion even on cold and slightly condensated glass surfaces, by using appropriate labelling systems and labelling set-up. Provides excellent ice-bucket resistance.

|                 |             |        |              |
|-----------------|-------------|--------|--------------|
| Tack:           | > 15        | N/25mm | FTM9 (Glass) |
| Peel (20 min.): | > 18        | N/25mm | FTM1 (Glass) |
| Cohesion:       | Medium/High |        | FTM8 (Inox)  |

**Liner: G74B**

White supercalandered glassine paper

|               |      |                   |           |
|---------------|------|-------------------|-----------|
| Basis weight: | 74   | gr/m <sup>2</sup> | ISO 536   |
| Thickness:    | 64   | µm                | ISO 534   |
| Transparency: | > 45 | %                 | DIN 53147 |

This product is made from certified papers FSC® - Lic. C164660 - Cert. n° INT-COC-001611

**Additional information:**

**This product is not recommended for labelling of small diameter and highly curved bottles, and not even for bottle neck labels. We recommend labels always facing out-side in the roll.**

Adhesion values make reference to tests on clean and dry glass surface, at standard room conditions of 23°C and 50% R.H. Ice -bucket resistance is meant by testing unprinted labels, after 48 hours bonding on clean and dry glass bottles. Overall condition of application and labelling systems, must be previously checked when cold, high humidity and condensation are involved, in order to prove the final result.

Keep the product at constant room conditions of approximately 20-25 °C and 40-50% R.H. (FINAT indication), avoiding exposition to heat and direct sunlight.

*Only the products indicated as such in this document are FSC® certified.*